

# BLUE HEAVEN 11mm

PRODUCT DATASHEET • ISSUE 10 - 09.02.23



## FEATURES

- MANUFACTURED IN THE UK TO BS EN 14499
- EXCELLENT THERMAL AND SOUND REDUCTION PROPERTIES
- EXCELLENT RECOVERY CHARACTERISTICS

## APPLICATIONS

- DOMESTIC INSTALLATIONS
- PRESTIGIOUS LUXURY USE AREAS
- AREAS WHERE A VERY HIGH DEGREE OF COMFORT IS REQUIRED

### STANDARD SPECIFICATIONS

CORE	APT core	
TOP SURFACE	White non-woven fabric with blue print	
BOTTOM SURFACE	White non-woven fabric	
NOMINAL THICKNESS	11.00 mm	
NOMINAL ROLL WEIGHT	18.0 kg	39.7 lb
WEIGHT PER UNIT AREA	1194 g/m <sup>2</sup>	35 oz/yd <sup>2</sup>
ROLL LENGTH	11.0 m	36.0 ft
ROLL WIDTH	1.37 m	54 in
CORE DENSITY	100 kg/m <sup>3</sup>	
PRODUCT DENSITY	108 kg/m <sup>3</sup>	

### BS EN 14499:2015 TEST RESULTS - UK AND EU STANDARD FOR CARPET UNDERLAYS

END USE CLASSIFICATION	BS EN 14499	L/U
WORK OF COMPRESSION AFTER 1000 IMPACTS	BS 4098	>150 J/m <sup>2</sup>
RETENTION OF WORK OF COMPRESSION	BS 4098	>70 %
LOSS IN THICKNESS AFTER STATIC LOADING	BS 4939 ISO 3416	<5.00 %
LOSS IN THICKNESS AFTER DYNAMIC LOADING	BS ISO 2094 (R05)	<5.00 %
RESISTANCE TO CRACKING	BS EN 14499	Pass

### INDOOR AIR QUALITY TEST

TESTED TO ISO 16000		
TESTED TO EUROFINS INDOOR AIR COMFORT® STANDARD	Pass	
TESTED TO EUROFINS INDOOR AIR COMFORT GOLD® STANDARD	Pass	
FRENCH VOC REGULATIONS	A+	
FRENCH CMR COMPONENTS	Pass	
ITALIAN CAM	Pass	
AgBB/ABG	Pass	
FORMALDEHYDE EMISSION CLASS	E1	
BREEAM INTERNATIONAL	Compliant	
LEED V4 (OUTSIDE U.S.)	Compliant	
BREEAM® NOR	Compliant	

### OTHER RELEVANT TESTS

THERMAL RESISTANCE (TOG RATING)	BS 4745	3.2 Tog
IMPACT SOUND IMPROVEMENT INDEX (TESTED / RATED)	BS EN ISO 10140-3 BS EN ISO 717-2	43-44 dB

### DISCLAIMER

Whilst every effort is made to ensure its accuracy, the data on this sheet is meant for information purposes only. The typical properties listed are the result of extensive laboratory tests, but since Ball & Young has no control over the end use of each material, we cannot guarantee these results are obtained in practice. Users should conduct their own tests to determine the suitability of each material to its intended application.